



Specification of Rubber Sheet

Description	General properties				Aging test (70 °C x 70h)			Compression set 70°C x 22h (%)	General Information
	Hs (Shore A)	T _B (kg/cm ²)	Pressure (PSI)	E _B (%)	ΔHs (Shore A)	ΔT _B (%)	ΔE _B (%)		
Netural Rubber Sheet	70 ± 5	40	1000	250	+10	-25	-35	50	General purpose with good all round